

ARMOUR PROOF COATINGS

Revised: 03.01.23

AP-5400 HIGH SOLIDS Silicone Roof Coating

PRODUCT DESCRIPTION

Armour Proof AP-5400 High Solids Silicone Roof Coating is an exciting, new high yield, low VOC one-part silicone elastomeric roof coating! It was specifically designed as a protective coating over a variety of roofing substrates. Once cured, this liquid applied silicone coating provides a durable, seamless, flexible, waterproof membrane that resists lateral movement, shear and will allow for normal expansion and contraction. **AP-5400 High Solids Silicone Roof Coating**, when compared mil for mil, provides greater UV protection than similar silicone coatings and offers increased resistance to moisture penetration. **AP-5400** provides excellent long term protection through exceptional weatherability properties.

TECHNICAL DATA

TOTAL SOLIDS BY VOLUME: 96% ± 2
WEIGHT PER GALLON: 10.7 lbs. per gallon
FLASH POINT: > 290° F
VISCOSITY: 4800 – 9000 cPs
TENSILE STRENGTH: 325 psi ± 50
ELONGATION: 249% ± 50
HARDNESS: 50 ± 5 Shore A
PERMEABILITY: 4.2 perms
SERVICE TEMPERATURE: -50° to 200° F
CLEAN UP: Solvent
ASTM: D2697

THINNER: Not Recommended
CURE TIME: 2 – 8 Hours
TACK FREE: 1 Hour
SKINOVER: 30 Minutes
SHELF LIFE: 6 months @ 35° – 75° F
VOC: Less than 50 g/l
SOLAR REFLECTANCE: 87%
THERMAL EMITTANCE: 89%
COLOR: White ○
PACKAGING: 5 Gallon Pail, 55 Gallon Drum

APPLICATION

AP-5400 High Solids Silicone Roof Coating may be applied by medium nap rollers, soft brushes or high pressure airless spray equipment. Apply **AP-5400** only to clean, dry, sound surfaces free of loose particles or other foreign matter. For best results, ambient temperature should be between 50-90°F. Higher temperatures will shorten the cure and working times for proper application of granules before the material has skinned. Lower temperatures will lengthen the skinover, tack free and ultimate cure time. Sudden temperature declines may also result in dew formation on surfaces, which can prevent adhesion development. For best results, relative humidity should be above 20%. Lower humidity will slow the cure time significantly. **For Airless Spray Application:** Minimum pump pressure 3000 psi, **Tip Size:** .027”-.039” (.031” recommended). **Hose:** Use 3/8” up to 100’, from 100’ to 200’ use 1/2” or larger

COVERAGE AND DRYING TIME

Apply **AP-5400** at the rate of 1.25 gallons per 100 sq. ft. Minimum dry mil thickness shall be above 20 mils. Two passes of silicone and a primer coat may be required for some applications and warranty programs. **PRODUCT APPLICATION SHOULD BE SUSPENDED IMMEDIATELY AND OUR TECHNICAL SERVICE PERSONNEL CONTACTED IF THE RESULTS BEING OBTAINED ARE LESS THAN DESIRABLE.** Refer to the Armour Proof Coatings Specification for detailed instructions.

PREPARATION OF SUBSTRATE

Surface must be pressure washed clean, free of all loose particles, dirt debris and other contaminants that could inhibit adhesion. An Armour Proof Primer may be required for the particular substrate. Refer to the Armour Proof Coatings Specification for detailed instructions on how to prepare the specific substrate.


LIMITATIONS AND PRECAUTIONS

Avoid contamination in sealed containers. Store away from heat and sources of ignition. Do not inhale vapor or mist; do not get on skin, in eyes or on clothing. Refer to SDS for more information.

LEARN MORE → UnitedAsphalt.com/AP5400



TOOLS NEEDED ▾



PACKAGING SIZES ▾



WARRANTY

This product will perform as claimed if directions are followed. Armour Proof Coatings cannot control conditions of application and substrate, or methods used. This warranty is limited to replacement of the defective material used, and does not include labor or labor costs.